



National Standard of the People's Republic of China

GB/T 14233.1-2008

Replacing GB/T 14233.1-1998

Test Methods for Infusion, Transfusion, and Injection

Equipments for Medical Use

Part 1: Chemical Analysis Methods

Issue Date: Nov. 3rd, 2008

Implementation Date: Oct. 1, 2009

Issued by **General Administration for Quality Supervision and Inspection and
Quarantine of the People's Republic of China, and China National Standardization
Administration Committee**

Table of Contents

Foreword	2
1 Scope	3
2 Referenced Standards	3
3 General Principles	3
4 Preparation of Test Solution.....	4
5 Analytical Methods for Test Solution Extraction.....	6
6 Analytical Methods for Total Heavy Metal in the Material	18
7 Analytical Methods for Content of Some Heavy Metal Elements in the Material	19
8 Burning Residue	20
9 Determination of Residual Ethylene Oxide –Gas Chromatography.....	21
10 Analysis of Residual Ethylene Oxide -- Colorimetric Analysis.....	23
Referenced Documents	26

Foreword

GB/T 14233 *Test Methods for Infusion, Transfusion, and Injection Equipmenst for Medical Use* consists of two parts:

- Part 1: Chemical Analysis Methods; and
- Part 2: Biochemical Test Methods.

This standard is Part 1 of GB/T 14233.

The Standard replaces GB/T 14233.1 – 1998 *Test Methods for Infusion, Transfusion, and Injection Equipmenst for Medical Use Part 1: Chemical Analysis Methods*. Given that GB/T 14233.1 – 1998 has been widely quoted in many product standards, the clause numbers in this Standard are kept as closely as possible to the original standard to avoid confusions caused by the change of clause No. in standard revision. The original clauses are altered wherever the alteration is necessary, and new amendments, followed by new methods, are numbered on the basis of the original serial number.

The Standards, as compared with GB/T 14233.1 – 1998, is mainly changed as follows:

- Solution Preparation methods and their description are revised;
- Two test solution preparation methods are added: one for irregular shaped and bulky products with short using time (less than 24 hours), another for irregular shaped products with long using time (more than 24 hours) and water-absorbing materials;
- Test methods for turbidity, color and luster are added;
- Test methods for the determination of chloride, pH value, heavy metal, ammonium, zinc, burning residue and residual ethylene oxide are revised;
- Test methods for atomic fluorescence spectrophotometry is added; and
- Test methods for sulfate are deleted.

The Standard is brought up by the State Food and Drug Administration.

The Standard resides with the National Standardization Technical Committee for Transfusion Equipments.

The Standard was mainly drafted by: Jinan Medical Device Testing Center, State Food and Drug Administration

Primary drafters of the Standard: Luo Hongyu, Pan Huaxian, Shi Yanping, Sun Guangyu, Li Kefang, Qin Dongli, Liu Bin, Liu Lili, and Guo Lun.

Replaced previous editions by the Standard are:

- GB/T 14233. 1 – 1993; and
- GB/T 14233. 1 – 1998.

Test Methods for Infusion, Transfusion, and Injection

Equipments for Medical Use

Part 1: Chemical Analysis Methods

1 Scope

Test methods for chemical analysis of infusion, transfusion, injection equipments for medical use are specified in this part of Standard GB/T 14233.

This part of Standard applies to chemical analysis of infusion, transfusion, injection and attached equipments for medical use that are made of medical polymer materials.

Chemical analysis of other medical polymer products can also refer to this Standard.

2 Referenced Standards

This part of Standard GB/T 14233 incorporates clauses of the following documents if they are quoted. If the references are dated, all the following lists of modifications (errata excluded) or revised editions thereof shall not be applicable to the Standards. However, parties concerned that have reached an agreement based on the Standards are encouraged to hold discussions on whether the latest editions of the said references can be adopted. Where the references are undated, the updated editions thereof shall apply to the Standards.

GB/T 601 *Chemical Reagents - Preparation of Standard Titrating Solution*

GB/T 6682 *Specifications on Water for Analytical Laboratory and Test Methods* (GB/T 6682 – 2008, ISO 3696: 1987, MOD)

Pharmacopoeia II of the People's Republic of China (2005 edition)

3 General Principles

3.1 All the analysis in the Standard is performed by two parallel test groups and the results should be within permissible relative deviation limits. The arithmetic average is used as experimental result. If only one test is qualified and the other one is not qualified, the arithmetic average calculation can't be calculated and the test should be performed again.

3.2 All the reagents in the Standard, unless specified otherwise, are all analytically pure.

3.3 Water for test use in the Standard, unless specified otherwise, should meet requirements for level II water in GB/T 6682.

3.4 The glossary 'room temperature' in the Standard refers to 10 – 30°C.

3.5 The glossary 'precisely weigh' in the Standard indicates weighing in precision 0.1mg.

3.6 The glossary 'precisely measure' in the Standard indicates measuring with transfer pipettes that meet the accuracy requirements specified in relevant national standards.

3.7 Weight law of permanence indicates weight difference of the test product after two times burning or drying is no more than 0.3mg.

3.8 All the glass containers in the Standard, unless specified otherwise, are all silicon borate glass containers.

4 Preparation of Test Solution

4.1 When preparing test solution, it's required to simulate as much as possible the conditions products undergo in use (such as application area, time, temperature, etc.). If using time of the product is a little long (more than 24h), it's recommended to prepare the test solution under accelerated test condition, but feasibility and reasonability of the methods should be verified.

4.2 The method of preparing test solution should be those that try every means to make all measurable surfaces of the samples extracted.

4.3 It's recommended to choose preparation methods of test solution from Table 1.

Table 1: Preparation Methods of Test Solution

No.	Preparation methods of test solution	Applicable products
1	3 sets of samples are chosen and they're connected to be a circular system with a glass flask. 250mL water is added and kept at temperature of 37°C±1°C. Through a wiggly pump operating on a silicon rubber tube for medical use, which is as short as possible, water is circulated at 1L/h for 2h. All liquid is collected and cooled to room temperature, which is to be used as test solution. Water of the same volume is placed into glass flask. Blank control solution is prepared according to the same method.	In vitro pipeline products with short using time (no more than 24h).
2	Cut samples into 1cm-long fragments and put them into a glass container. Add water and make sure that the ratio of entire surface area of inside and outside sample (cm ²) and	In vivo catheters with short using time (no more than 24h)